



Skyzon® Basic Dyes



No.	Color Sample	Skyzon® Basic Dye	C.I. Basic NO.	Dyeing Depth (O.W.F)	k.Compatible value	PH Stable Range	Light (Xenon)	1500 15L/ton	Washing			Rubbing		Perspiration		
									Changein Shade	Stained on cotton	Stained on Acrylic	Dry	Wet	Changein Shade	Stained on Cotton	Stained on Acrylic
1		Yellow X-8GL 250%	Y-13	0.90	3.5	2-5	6-7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4
2		Golden Yellow X-GL 250%	Y-28	0.75	3.5	3-6	6-7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
3		Brill.Flavine 10GFF 300%	Y-40	0.5	3.5	2-5	3	4-5	4-5	4-5	4-5	5	5	4-5	4-5	4-5
4		Pink X-FG 250%	R-13	1	4.0	3-7	3-4	4	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5
5		Brill.Red X-5GN 250%	R-14	0.72	3.5	2-7	3-4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
6		Red X-GTL 200%	R-18	0.4	3.0	2-10	5	4	4	4-5	4-5	4-5	4-5	3-4	4-5	4-5
7		Red X-GRL 250%	R-46	0.8	3.5	2-7	6-7	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5
8		Red 3R 300%	V-16	0.53	1.5	3-8	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
9		Turquoise Blue X-GB 250%	B-3	0.36	3.5	3-8	4-5	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5
10		Blue X-GRL 300%	B-41	0.4	3.5	2-5	6	3-4	4	4-5	4-5	4-5	4-5	4	4-5	4-5
11		Blue X-GRRL 250%	B-41:1	0.4	3.5	2-5	6	3-4	4	4-5	4-5	4-5	4-5	4	4	4-5
12		Blue X-BL 250%	B-159	0.36	3.5	2-7	6-7	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
13		Black FBL 200%	/	2	3	2-7	6	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4
14		Black SW 500%	/	1.5	3.0	3-6	5	4-5	3-4	4	4	4-5	4-5	4	3-4	4
15		Black X-O 300%	/	1.5	3.0	3-6	5	4-5	3-4	4	4	4-5	4-5	4	3-4	4